

## CLAIMS

---

[Claim(s)]

[Claim 1] The paper carton with which the consistency of paper is characterized by the rigidity of 0.60 - 0.95 g/cm<sup>3</sup> and a longitudinal direction being per [ 0.4 ] micrometer in thickness - 0.9 gf-cm in the paper carton which consists of a layered product of the resin layer and paper containing the layer of the polyamide resin generated at the polycondensation reaction of meta-xylylene diamine and an adipic acid.

[Claim 2] The paper carton according to claim 1 characterized by being that in which paper contains the pulp obtained from the needle-leaf tree 40% of the weight or more.

[Claim 3] The paper carton according to claim 1 or 2 characterized by containing or applying the polyethyleneimine system under coat agent to paper.